

Örnek (Sample): Panetti 5mm Standart Seri "S" PN5 – 1

Örnek (Sample)	Boy (Length) (mm)	Genişlik (Width) (mm)	Kalınlık (Thickness) (mm)
1	50.14	50.66	4.81
2	51.00	51.55	4.82
3	51.07	50.74	4.88
4	51.16	50.98	4.90
5	51.14	49.75	4.85



Sample	Basma Gerilmesi altında Akma Mukavemeti (Yield Strength under Compressive Stress) (N/mm ²)	%10 Deformasyonda Basma Gerilmesi (Compressive Stress at %10 Deformation) (N/mm ²)	Elastik Modül (Elastic Modulus) (N/mm ²)
1	0.170	0.232	4.11
2	0.161	0.220	3.75
3	0.172	0.231	4.24
4	0.179	0.226	3.85
5	0.181	0.235	4.06
Ort. (Avg.)	0.172	0.229	4.00
Std Sap. (St. Dev.) (±)	0.008	0.006	0.19

innoma
İnnoma İnovatif Malzeme Teknolojileri San. ve Tic. Ltd. Şti.
İzmir Teknoloji Geliştirme Bölgesi
İYTE, Gülbahçe Kampüsü, 35420 Urla-İZMİR, TURKEY
Tel - Fax: (228) 765 92 91
www.innoma.com.tr e-posta: info@innoma.com.tr
Tic.Sic.No İZMİR-194338 MERSİS No: 8395635842523250
URLA V.D. - 478 055 4463

Örnek (Sample): Panetti 5mm Standart Seri "S" PN5 – 2

Örnek (Sample)	Boy (Length) (mm)	Genişlik (Width) (mm)	Kalınlık (Thickness) (mm)
1	51.00	49.96	4.88
2	50.92	49.33	4.87
3	49.94	50.45	4.83
4	50.46	50.54	4.81
5	49.95	51.15	4.85

Örnek (Sample)	Basma Gerilmesi altında Akma Mukavemeti (Yield Strength under Compressive Stress) (N/mm ²)	%10 Deformasyonda Basma Gerilmesi (Compressive Stress at %10 Deformation) (N/mm ²)	Elastik Modül (Elastic Modulus) (N/mm ²)
1	0.196	0.240	4.02
2	0.183	0.235	4.22
3	0.182	0.232	3.99
4	0.183	0.225	3.46
5	0.184	0.226	3.52
Ort. (Avg.)	0.186	0.232	3.85
Std Sap. (St. Dev.) (±)	0.006	0.006	0.33



innoma
İnnoma İnovatif Malzeme Teknolojileri San. ve Tic. Ltd. Şti.
İzmir Teknoloji Geliştirme Bölgesi
İYTE, Gülbahçe Kampüsü, 35330 Urla-İZMİR, TURKEY
Tel - Fax: (232) 765 9241
www.innoma.com.tr - e-posta: info@innoma.com.tr
Tic.Sic.No İZMİR-184338 MERSİS No: 8395635042523250
URLA V.D. • 478 055 4463